

No. AJHL1610011324FB-2

Date: OCT.24, 2016

Page 1 of 6

POSTER AND PANEL

C/PERE ANDORRA, S/N, POL. IND, ILLA, SUD, NAUS, 4, 5, 16,08650, SALLENT, BARCELONA, SPAIN

The following sample(s) was / were submitted and identified on behalf of the client as:

Sample Description: Textil Tango Opaque greyback 260gr

<u>Color</u>: WHITE <u>Thickness</u>: 260μM <u>Density</u>: 200GSM

Composition: 55% POLYESTER, 45% COATING

<u>Supplier</u>: POSTER AND PANEL <u>Country of Destination</u>: EUROPE

End Use Application: INKJET MEDIA

Test Requested:

To determine the flammability (building materials class B1) in accordance with DIN 4102-1 (May 1998)

Fire behaviour of building materials and elements Part 1: Classification of building materials,

Requirements and testing

Test Results: -- See attached sheet -

Classification: The tested sample meets class B1 building materials requirements of DIN 4102-1 (May

1998).

Test Period:

Sample Receiving Date : OCT.08, 2016

Test Performing Date : OCT.08, 2016 TO OCT.24, 2016

Signed for and on behalf of SGS-CSTC Co., Ltd. Anji Branch



Technical Manager



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <a href="http://www.sgs.com/en/Terms-and-Conditions.aggs.and.forelectronic Documents at http://www.sgs.com/en/Terms-and-Conditions-and-Conditions-and-Cond



No. AJHL1610011324FB-2

Date: OCT.24, 2016

Page 2 of 6

Test conducted

This test was conducted as per DIN 4102-15:1990 DIN 4102-16:1998 and DIN 4102-1:1998 Clause 6.2, and Classification in according to DIN 4102-1 (May 1998) Clause 6.1-Class B1 materials.

II. Sample details

General description / Color	COATED POLYESTER FABRIC /					
Density	About 200 g/m ₂					
Size of sample	1000mm×190mm & 190mm×90mm					

Conditioning

Prior to testing, the sample was conditioned at least 14 days to constant mass at a temperature of 23 \pm 2 °C, and a relative humidity of 50 \pm 6 %.

- III. Test results
- 1) "Brandschacht" Test according to DIN 4102-15 &16

Exposed surface: The front face

Results of "Brandschacht" Test (part 1)								
Line		Unit	Test assemblies No.					
No.		Offic	Lengthwise	Widthwise				
1	Specimen fixings according to DIN 4102 part 15, table	/						
2	Max. flame height above lower sample edge;	cm	50	50				
3	Time 1)	min:s	0:15	0:18				
	Melting/burning through							
4	Time 1)	min:s	0:03	0:04				
	Back of specimen							
5	Flaming/glowing, Time 1)	min:s	0:02	0:03				
6	Discolouring, Time 1)	min:s	0:04	0:05				
	Burning droplets							
7	Begin 1)	min:s	0:06	0:08				
	Amount							
8	Specimen material falling off in separate droplets		/	/				
9	Specimen material falling off continuously		√	√				

To be continued...



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printe overleaf, available on request or accessible at http://www.ags.com/en/Terms-and-Conditions.ags; and, for electronic format documents subject to Terms and Conditions for Electronic Documents at http://www.ags.com/en/Terms-and-Conditions/Terms-and-Conditions against the subject to Terms and Conditions for Electronic Documents and Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's Indiaga at the time of is intervention only and within the limits Cilient's instructions, if any. The Company's sole responsibility is to its Cilient and this document does not exonerate parties to transaction from exercising all their rights and obligations under the transaction document does not exonerate parties to transaction from exercising all their rights and obligations under the transaction document common to be reproduce except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content of appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) sested and such sample(s) are retained for 30 days only.



No. AJHL1610011324FB-2

Date: OCT.24, 2016

Page 3 of 6

Results of "Brandschacht" Test (part 2)							
Line		Unit	Test assemblies No.				
No.			Lengthwise	Widthwise			
	Burning parts						
10	Begin 1)	min:s	0:12	0:15			
11	Parts of sample falling off separately		√	\checkmark			
12	Parts of sample falling off continuously		/	/			
13	Duration of continued combustion on mesh base (max.)	min:s	No	No			
	Burner flame impairment by dripping/falling material		No	No			
14	Time 1)	min:s	/	/			
	Premature ending of test		/	/			
15	End of burning at specimen 1)	min:s	/	/			
16	Time when test terminated (if applicable) 1)		/	/			
	Burning after end of test		No	No			
17	Duration	min:s	/	/			
18	Number of specimens		/	/			
19	Front of specimen		/	/			
20	Back of specimen		/	/			
21	Height of flame	cm	/	/			
	Glowing after end of test		No	No			
22	Duration	min:s	/	/			
23	Number of specimens		/	/			
24	Front of specimen		/	/			
25	Back of specimen		/	/			
26	Top half of specimen		/	/			
27	Bottom half of specimen		/	/			

To be continued...



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printe overlead, available on request or accessible at http://www.sps.com/en/ferms-and-Conditions.agr, and, for electronic format documents subject to Terms and Conditions (Ferms-Documents) and that the company of th

No. 301, Sunlight Road, 2 Block, Sunlight Industry Zone, Anj County, Zhejiang Province, China 313300 t (多元72) 503825 f (多元72) 503825 www.sgsgroup.com.cn 中国 - 浙江 - 安吉县阳光工业园二区阳光大道301号 邮箱:313300 t (多元72) 503825 f (多元72) 503829 e sgs.china@sgs.com



No. AJHL1610011324FB-2

Date: OCT.24, 2016

Page 4 of 6

Results of "Brandschacht" Test (part 3)								
Line		Unit	Test assemblies No.					
No.		J	Lengthwise		Widthwise			
	Residual length							
28	Single results	cm	54	57	55	57		
20		cm	52	53	56	57		
29	Average of the single results	cm	54.0		56.3			
	Smoke temperature							
30	Max. of average	$^{\circ}$	146.2		145.4			
31	Time 1)	min:s	06:55		07:12			

Note: 1) time from start of testing

Class B1 materials:

If the residual length measured after the first test is 45cm or greater, further tests are not required.

2) Normal Flammability Test according to DIN 4102-1 Clause 6.2

<u>Flame application:</u> [$\sqrt{\ }$] bottom edge ignition, [] surface ignition

Parameter	Lengthwise					Crosswise				
	1	2	3	4	5	6	7	8	9	10
Reaching the measuring mark within 20 seconds(Yes/No)	No	No	No	No	No	No	No	No	No	No
Self extinguishing of the flame (s)	15	15	15	15	15	15	15	15	15	15
Max. flame height (cm)	5	6	6	5	5	4	5	5	4	5
End of afterflaming (s)	15	15	15	15	15	15	15	15	15	15
End of afterglowing (s)	15	15	15	15	15	15	15	15	15	15
Molten dripping(Yes/No)	No	No	No	No	No	No	No	No	No	No
Smoke developments (visual impression)	Slight					Slight				

All timings are from start of testing.

To be continued...



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <a href="http://www.sgs.com/en/Terms-and-Conditions.aggs.and.forelectronic Documents at http://www.sgs.com/en/Terms-and-Conditions-and-Conditions-and-Cond

^{*}Reduction in number of test (DIN 4102 Part 16, clause 5.2)



No. AJHL1610011324FB-2

Date: OCT.24, 2016

Page 5 of 6

- IV. DIN 4102-1:1998 Criteria for classification
- 1) All materials, except flooring, may be classed as B1 materials if they meet the following requirements a) and b):
- a) The test using the 'Brandschacht' apparatus described in DIN 4102-15 (cf. subclause 6.1.3.1) shall be deemed passed if
- The mean value for the residual length (portion of specimen that has not burned or charred; cf. subclause
- 9.1 of DIN 4102-16) of each specimen is at least 15 cm and no individual values are lower than 0 cm,
- The mean effluent temperature does not exceed 200 °C in any test,
- The requirement for the residual length of each specimen is met even where there is afterflame, afterglow, or smouldering.
- b) Pass DIN 4102-1: 1998 sub-clause 6.2.3 Ignitability Test if For each specimen, flaming doesn't reach the gage mark within 20s after flame application.
- 2) Materials may be classed as B2 materials if they pass the ignitibility test specified in DIN 4102-1: 1998 subclause 6.2.5.

For each specimen, flaming doesn't reach the gage mark (150mm marks) within 20s after flame application.

3) Combustible materials which cannot be classed as B1 or B2 materials shall be classed as B3 materials.

STATEMENTS:

This test report does not replace any mandatory certification of the product that may be required.

The test results relate to the behaviour of the test specimens of a product under the particular conditions of the test; they are not intended to be the sole criterion for assessing the potential fire and smoke hazard of the product in use.

To be continued...





No. AJHL1610011324FB-2

Date: OCT.24, 2016

Page 6 of 6

Photo Appendix:



SGS authenticate the photo on original report only

*** End of Report ***

