

Test Report NO. AJHL1702001705FB-01 Date: MAR.30, 2017 Page 1 of 6

POSTER AND PANEL S.L.

P. I Plans de la Sala, C/Plans de la Sala, 28, 08650, Sallent, Spain

THIS TEST RESULT IS COPIED FROM THE TEST REPORT No.: AJHL1702001705FB, DATE: MAR.20, 2017

The following sample(s) was / were submitted and identified on behalf of the client as:

Sample Description: PVC COATED MESH

Color: WHITE Density: 270G/M²

Test Requested:

To determine the flammability (building materials class B1) in accordance with DIN 4102-1 (May 1998) Fire behaviour of building materials and elements Part 1: Classification of building materials, Requirements and testing

Test Results: -- See attached sheet --

Classification: The tested sample meets class B1 building materials requirements of DIN 4102-1 (May

1998).

Test Period:

Sample Receiving Date : MAR.01, 2017

Test Performing Date : MAR.01, 2017 TO MAR.16, 2017

Signed for and on behalf of SGS-CSTC Co., Ltd. Anji Branch

Allen Zou

Technical Manager





NO. AJHL1702001705FB-01 Date: MAR.30, 2017 Page 2 of 6

Test conducted

This test was conducted as per DIN 4102-15:1990 DIN 4102-16:1998 and DIN 4102-1:1998 Clause 6.2, and Classification in according to DIN 4102-1 (May 1998) Clause 6.1-Class B1 materials.

II. Sample details

General description / Color	PVC COATED MESH / White
Density	About 270 g/m ²
Size of sample	1000mm×190mm & 190mm×90mm

Conditioning

Prior to testing, the sample was conditioned at least 14 days to constant mass at a temperature of 23 \pm 2 °C, and a relative humidity of 50 \pm 6 %.

III. Test results

1) "Brandschacht" Test according to DIN 4102-15 &16

Exposed surface: The front face

	Results of "Brandscha	acht" Tes	t (part 1)					
Line		Unit	Test assemblies No.					
No.		Offic	Α	В	С	D		
1	Specimen fixings according to DIN 4102 part 15, table	<u>u</u>	44					
2	Max. flame height above lower sample edge;	cm	40					
3	Time 1)	min:s	0:05					
	Melting/burning through							
4	Time 1)	min:s	0:04					
	Back of specimen							
5	Flaming/glowing, Time 1)	min:s	0:04					
6	Discolouring, Time 1)	min:s	0:03					
	Burning droplets		NO					
7	Begin 1)	min:s	1					
	Amount		/					
8	Specimen material falling off in separate droplets		1					
9	Specimen material falling off continuously		/					

To be continued...



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sgs.com/en/Terms-and-Conditions asox and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Document.asox.
Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document asox advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction form exercising all their rights and obligations under the transaction document. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fulless extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

**Attention-To-check the authenticity of testing inspection report & certificate and except context us at telephone (86-755) 8307.

Attention: To check the authenticity of testing / inspection report & certificate, please contact us at telephone: (86-755) 830: 1443, or email: CN.Doccheck@sps.com

No. 301 Suided David Stock Suided belate Zero And Courte Zealand Davidso China 34:3300. + (95-579) 50100% (46-579) 50100% (46-579) 50100%



NO. AJHL1702001705FB-01 Date: MAR.30, 2017 Page 3 of 6

	Results of "Brandscha	acht" Tes	t (part 2)					
Line No.		Unit	Test assemblies No.					
IVO.	D		A	В	С	D		
	Burning parts	*******************************						
10	Begin 1)	min:s	0:53					
11	Parts of sample falling off separately		√					
12	Parts of sample falling off continuously							
13	Duration of continued combustion on mesh base (max.)	min:s	NO					
	Burner flame impairment by dripping/falling material		NO					
14	Time 1)	min:s	/					
	Premature ending of test		7					
15	End of burning at specimen 1)	min:s	/					
16	Time when test terminated (if applicable) 1)	min:s	/					
	Burning after end of test		NO					
17	Duration	min:s	/					
18	Number of specimens		/					
19	Front of specimen		/					
20	Back of specimen		/					
21	Height of flame	cm	/					
	Glowing after end of test		NO					
22	Duration	min:s	1					
23	Number of specimens		/					
24	Front of specimen		/					
25	Back of specimen		1					
26	Top half of specimen		/					
27	Bottom half of specimen		/					

To be continued...



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sgs.com/en/Terms-and-Conditions.aggv.and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <a href="http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Document.aggv.atendors.aggv.and-conditions/Terms-e-Document.aggv.atendors.aggv.and-conditions/Terms-e-Document.aggv.atendors.aggv.and-conditions/Terms-e-Document.aggv.atendors.aggv.and-conditions/Terms-en/Conditions/Terms-e-Document.aggv.atendors.aggv.aggv.and-conditions/Terms-en/Conditions/Terms-e-Document.aggv.atendors.aggv.and-conditions/Terms-en/Conditions/Terms-e-Document.aggv.atendors.aggv.and-conditions/Terms-en/Conditions/Terms-e-Document aggv.atendors.aggv.and-conditions/Terms-en/Conditions/Terms-e-Document.aggv.and-conditions/Terms-en/Conditions/Terms-e-Document.aggv.atendors/Terms-e-Docum



NO. AJHL1702001705FB-01 Date: MAR.30, 2017

Page 4 of 6

Line		Unit	Test assemblies No.					
No.		Offic	Α		В	С	D	
	Residual length					4:		
28	OO Single we sulte	am	65	66				
28 Single results	cm	64	68					
29	Average of the single results	cm	65	5.8				
	Smoke temperature							
30	Max. of average	°C	14	1.2				
31	Time 1)	min:s	06:58					

Note: 1) time from start of testing

Class B1 materials:

If the residual length measured after the first test is 45cm or greater, further tests are not required.

2) Normal Flammability Test according to DIN 4102-1 Clause 6.2

Flame application: [✓] bottom edge ignition, [] surface ignition

Darameter		Lengthwise						
Parameter	1	2	3	4	5			
Whether or not flaming extinguished before reach the gauge mark(Yes/No)	Yes	Yes	Yes	Yes	Yes			
Whether or not flaming reach the measuring mark within 20 seconds(Yes/No)	No	No	No	No	No			
Time for the flame tip to reach the gauge mark(s)	No	No	No	No	No			
Time of flaming extinguished from fire application (s)	0	0	0	0	0			
Max. flame height (cm)	8	10	12	9	8			
Molten dripping(Yes/No)	No	No	No	No	No			
Smoke developments (visual impression)	Slight			1.				

Note:

NA---Not applicable

To be continued...



No. 301, Sunlight Road, 2 Block, Sunlight Industry Zone, Anji County, Zhejiang Province, China 313300 t (%5-572) 5018825 f (%5-572) 5018829 www.sgsgroup.com.cn 中国·浙江·安吉县阳光工业园二区阳光大道301号 邮编:313300 t (86-572) 5018825 f (86-572) 5018829 e sgs.china@sgs.com

^{*}Reduction in number of test (DIN 4102 Part 16, clause 5.2)



Test Report NO. AJHL1702001705FB-01 Date: MAR.30, 2017 Page 5 of 6

DIN 4102-1:1998 Criteria for classification

- 1) All materials, except flooring, may be classed as **B1** materials if they meet the following requirements a) and b):
- a) The test using the 'Brandschacht' apparatus described in DIN 4102-15 (cf. subclause 6.1.3.1) shall be deemed passed if
- The mean value for the residual length (portion of specimen that has not burned or charred; cf. subclause
- 9.1 of DIN 4102-16) of each specimen is at least 15 cm and no individual values are lower than 0 cm,
- The mean effluent temperature does not exceed 200 °C in any test,
- The requirement for the residual length of each specimen is met even where there is afterflame, afterglow, or smouldering.
- b) Pass DIN 4102-1: 1998 sub-clause 6.2.3 Ignitability Test if
 For each specimen, flaming doesn't reach the gage mark within 20s after flame application.
- Materials may be classed as B2 materials if they pass the ignitibility test specified in DIN 4102-1: 1998 subclause 6.2.5.

For each specimen, flaming doesn't reach the gage mark (150mm marks) within 20s after flame application.

3) Combustible materials which cannot be classed as B1 or B2 materials shall be classed as B3 materials.

STATEMENTS:

This test report does not replace any mandatory certification of the product that may be required.

The test results relate to the behaviour of the test specimens of a product under the particular conditions of the test; they are not intended to be the sole criterion for assessing the potential fire and smoke hazard of the product in use.

To be continued...




Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service prints overleaf, available on request or accessible at http://www.sga.com/en/Terms-and-Conditions.aspy and, for electronic format document subject to Terms and Conditions for Electronic Documents at http://www.sga.com/en/Terms-and-Conditions/Terms-e-Document.asp Attention is drawn to the limitation of illability, indemnification and jurisdiction issues defined therein. Any holder of this document advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduce except in full, without prior written approval of the Company, Any unauthorized alteration, forgery or falsification of the content appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated it results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Attention: To check the authenticity of testing / inspection report & certificate, please contact us at telephone; 85-75) 834



NO. AJHL1702001705FB-01 Date: MAR.30, 2017 Page 6 of 6

Photo Appendix:



SGS authenticate the photo on original report only

End of Report



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sgs.com/en/Terms-and-Conditions.aspx.and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Document.aspx.attention in side and the limitation of liability, indemnification is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Attention:To check the authenticity of testing / inspection report & certificate, please contact us at telephone:186-7551 a307