



ENCAPSULADO ULTRAMATT 38MIC

Composition:

Hard coating (Matt): 4 mic

PET: 12 mic

EVA: 22mic

Aplication:

Protection for documents, photographs, color laser copies, color printing, posters, textiles, wood, etc.

Product properties:

| FEATURES | VALUE | TEST METHOD |
|-------------------------|---------------|-----------------------------|
| OPTICAL DATA | | |
| Transmittance | 89% | ASTM E 1164 |
| Reflectance | 10% | ASTM E 1164 |
| Haze (after lamination) | 65% | ASTM D 1003 |
| Whiteness | 93% | ASTM E 313-1973 |
| PHYSICAL DATA | | |
| Heat Shrinkage | 1.0 ± 0.3% MD | ASTM D 1204 (120°C / 15min) |
| | 1.2 ± 0.3% TD | |
| Glue Melting Point | 88°C | ASTM D 1204 (120°C / 15min) |
| Lamination Temperature | 90 - 100 | ASTM D 3418 |
| Surface Wetting Tension | 45 ± 2 | ASTM D 2578 |

Available measurements

PL692050 - Encapsulado Ultra Matt 38mic 1,55x300m

